


# OPTIGREEN TWB 1.0

## Root Protection Membrane

For placing on non-rootproof waterproofing using the solvent welding or hot air procedure as root protection under roof greening as well as for waterproofing for ponds and water tanks.



<b>Material</b>	PVC-P
<b>Nominal thickness</b>	Approx. 0.95 mm
<b>Grammage</b>	Approx. 1.29 kg/m <sup>2</sup>
<b>Colour</b>	Olive green
<b>Resistant to bitumen</b>	No
<b>Resistant</b>	- Up to 30°C continuous water temperature - To roots and microorganisms
<b>Tear strength vertically and horizontally</b>	17 (±2) N/mm <sup>2</sup>
<b>Resistance to tear propagation vertically and horizontally</b>	≥ 40 kN/m
<b>Elongation at break vertically and horizontally</b>	≥ 280 %
<b>Bursting resistance</b>	≥ 50 %
<b>Puncture resistance</b>	1.10 (±0.15) kN
<b>FLL tested</b>	Yes
<b>Delivery weight</b>	Approx. 51.6 kg/roll Approx. 900 kg/pallet
<b>Pack size</b>	Diameter approx. 0.20 m, height approx. 2.0 m / per roll
<b>Quantity/delivered unit</b>	2.0 x 20.0 m = 40.0 m <sup>2</sup> / roll 17 rolls = 680 m <sup>2</sup> per pallet
<b>Delivery form</b>	On a roll by forwarding agent, or on a disposable pallet 2.0 x 1.2 m

### Area of use

- As a root barrier membrane under green roofs on roof areas with waterproofing that is not root-proof (note: not approved as waterproofing)
- As a root-proof lining for planting troughs
- As waterproofing for ponds
- As waterproofing for water tanks

### Specific properties

- Resistant up to 30°C continuous water temperature
- Optimised tensile strength and elongation at break
- High ability to bridge tears
- UV-stabilised
- Resistant to roots and microorganisms
- High ageing resistance
- Flexible at low temperatures
- Dimensionally stable
- Can be laid on a damp base
- Can be solvent-welded
- Without DEHP (DOP) plasticisers
- Not resistant to bitumen

The preceding details are guideline values established under laboratory conditions. These values are subject to a certain manufacturing tolerance. The data contained in this product information sheet represents Optigreen's technical knowledge at the time of publication. Optigreen reserves the right to change and update details in accordance with new insights and to modify specified properties accordingly. No liability accepted for misprints.

#### Optigrün international AG

Am Birkenstock 15 – 19,  
72505 Krauchenwies-Göggingen  
Tel. +49 7576 772-0, Fax +49 7576 772-299, info@optigruen.de

#### Optigreen Limited (Service UK only)

Suite G5 Albany Chambers, 26 Bridge Road East  
Welwyn Garden City (Herts), AL7 1HL  
Phone +44 203 5899400, Fax +44 207 1171664, info@optigreen.co.uk

